

Intermiscibility Of Hose Description

软管内胶、接头材质与化学物质的相容性 Intermiscibility of Hose lining, fitting material, chemical substances

E=excellent 优秀的 C=conditional 限定条件下使用的 U=unsatisfactory 不适用的 G=good 好的		三元乙丙橡胶 EPDM	合成橡胶 Synthetic Rubber	铁氟龙 Teflon	热塑性橡胶 Thermoplastic Elastomer	钢Steel	黄铜Brass	不锈钢 Stainless Steel
Fluid	流体	Hose 软管				金属Metal		
soy bean oil	豆油	U	G	E	G	E	E	E
stannic chloride	氯化锡	E	E	E	C	U	U	U
steam (up to 388° F)	水蒸汽(最高388° F)	E	U	E	U	E	E	E
stearic acid	硬脂酸	E	G	E	G	C	C	E
styrene	苯乙烯	U	U	E	U	E	E	E
sulfur	硫	E	C	E	G	E	U	G
sulfur chloride	氯化硫	U	U	E	-	G	-	G
sulfur dioxide	二氧化硫	E	U	E	U	E	G	G
sulfur trioxide	三氧化硫	E	U	E	U	G	C	G
sulfuric acid (over 10%)	硫酸(超过10%)	U	U	E	U	C	C	U
sulfuric acid (to 10%)	硫酸(最高10%)	E	U	E	U	U	G	C
sulfurous acid	亚硫酸	E	C	E	U	U	C	C
tannic acid	丹宁酸	E	E	E	G	E	E	E
tar (bituminous)	柏油	U	C	E	G	E	G	E
tartaric acid	酒石酸	E	G	E	G	U	C	C
tertiary butyl alcohol	叔丁醇	E	G	E	G	G	G	G
titanium tetrachloride	四氯化钛	U	U	E	-	E	U	G
toluene (toluol)	甲苯	U	U	E	U	E	E	E
trichlorethylene	三氯乙烯	E	U	E	U	E	G	E
tricresyl phosphate	磷酸三(邻甲苯酯)	E	U	E	U	E	-	C
triethanolamine	三乙醇胺	E	C	E	U	E	U	E
tung oil	桐油	U	G	E	C	E	G	E
turpentine	松节油	U	C	E	G	G	G	G
varnish	清漆	U	C	E	G	E	G	E
vinyl chloride	氯乙烯	U	U	E	U	E	U	C
water (+151° F to +200° F)	水(151° F 到200° F)	E	G	E	U	C	G	E
water (+201° F to +350° F)	水(201° F 到350° F)	E	U	E	U	C	G	E
water (to +150° F)	水(最高150° F)	E	E	E	E	C	G	E
xylene	二甲苯	U	U	E	C	E	E	E
zinc chloride	氯化锌	E	E	E	E	E	U	U
zinc sulfate	硫酸锌	E	E	E	-	U	C	G